TECHNICAL DATA SHEET

Parquets





Parquets

Le Tonkinois Parquets is an open-pore varnish with very good penetration. The penetration of the oil into the capillaries of the wood, greatly reduces swelling and shrinkage and thus forms a durable good protection against abrasion, wear and has a high UV resistance.



Product description

Application area

Le Tonkinois Parquets is the perfect protection for any interior wood, preserves the natural, warm character of the wood for almost indefinitely. Natural surfaces impress with their beautiful wood grain, which is further fueled by Le Tonkinois.

Processing

Processing	Adjusted ready for use. Stir well before use. Do not dilute. Apply with brush, flat brush or spray. Depending on the type of wood, at least 2 - 3 coats are recommended. For sanding work such as intermediate sanding, a maximum of 180 grit is sufficient. Do not apply at temperatures below 12°C. Always apply thin coats by rolling or brushing and apply only one coat daily. Thoroughly sand or abrade parquet or floorboards. Priming and intermediate coats can be applied in one day, depending on drying. Final coat on the next day. In case of very soft woods, it is recommended to apply the primer coat with Bio Impression, as this oil penetrates very deeply, closes capillaries and hardens the wood. The coating is applied with a floor varnishing roller in thin layers.
Usage	30 - 50 ml/m², 20m²/liter, per coat depending on surface condition and absorbency of the substrate, based on smooth and planed/sanded surfaces. Absorbent substrates may result in higher consumption values for the first coat.
Drying time	At 20°C and medium humidity after 6 - 8 hours; if possible wait 24 hours for recoating. Low temperatures, high humidity and low air exchange delay drying and promote odor formation. Ensure good ventilation during application. Load surfaces only carefully at first.

Stand: 30.07.2024 www.le-tonkinois.com Seite 1 von 2

TECHNICAL DATA SHEET

Parquets



Substrates and their pretreatment

Underground

Untreated wood, wood-based materials, also on cork to a limited extent. Carefully sand wooden substrates. The wood surface must be free of dust and grease, clean, dry and frost-free (max. 15% wood moisture).

Product information

Ingredients	Linseed oil, tung oil, natural resins, isoaliphates
VOC Safety Notice	The VOC content of this product is max. 400 g/l. EU limit 500 g/l.
Storage	Store well closed, dry, cool, but frost-free.
Shelf life	Shelf life min. 5 years in unopened original container.
Disposal	Dispose of product residues and packaging in accordance with local regulations. Only recycle empty cans.
Safety instructions	For safety-relevant information, please refer to the corresponding safety data sheet.

Fon: +49-(0)30-34655745

To achieve optimum results, please observe the technical data sheets of all products used.

The information is based on our current knowledge and experience. However, they do not constitute a guarantee of product properties and do not establish a contractual legal relationship. With the publication of this Technical Data Sheet, all previous information becomes invalid.